



PRODUCT SPECIFICATION

Elastoseal H / T

Issued: 2009-11-27
Revision of: 2004-10-25

PHYSICAL PROPERTIES	UNIT	REQUIREMENTS	TYPICAL VALUE	TEST METHODS
Hardness	°IRH	65 ± 5	65	ISO 48
Tensile strength	MPa	min 9.0	9.8	ISO 37
Elongation at break	%	min 300	530	ISO 37
Tear strength	kN/m	min 30	43	ISO 34
Foldability at low temperature	°C	max -40	-60	EN 495-5

SealEco

Tel: +46 (0) 370 481 00

Fax: +46 (0) 370 485 00

Email: info@sealeco.com

Internet: www.sealeco.com

Office Address: Kävsjövägen 38,
SE-331 35 Värnamo, Sweden

Post Address: Box 514,
SE-331 25 Värnamo, Sweden

Org. No. 556739-6980